

PANDOMO® TerrazzoFiller

Additive for filling pores in PANDOMO® Terrazzo Systems

- Solidifies PANDOMO® TFW or the grinding dust in the pores of PANDOMO® Terrazzo systems.
- Improves in combination with PANDOMO® TerrazzoHardener the properties regarding abrasion resistance, surface hardness, chemical resistance and impact strength
- · Odourless and solvent-free



Application:

PANDOMO® TerrazzoFiller is used in the production of ground or polished PANDOMO® Terrazzo floors/systems.

PANDOMO® TerrazzoFiller improves the floor covering and, in combination with PANDOMO® TerrazzoHardener, leads to significantly more gloss and improved properties in terms of abrasion resistance, surface hardness, chemical resistance and impact resistance.

Properties:

PANDOMO® TerrazzoFiller consists of high-quality polymers

Application on PANDOMO® Terrazzo surfaces:

The surface must be finely sanded before application. PANDOMO® TerrazzoFiller with water mix up to a ratio of 1:4, 1:5, depending on the absorbency of the floor.

Mist/spray the finished mixture onto the surface with a pump sprayer and sprinkle on PANDOMO® TFW with a sieve. Move the trowel plate over the surface and distribute and work in the two components until the pores are closed.

A fine film should appear on the surface, the aggregates (grain size) in the PANDOMO $^{\otimes}$ Terrazzo should still be visible.

Remove excess material with a broom.

The surface should be treated again with PANDOMO® TerrazzoHardener.

The next day, the surface is wet sanded.

If there are still more pores open, the process should be repeated as described above.

Another option is to sand the surface.

When sanding the surface, PANDOMO® TerrazzoFiller is sprayed onto the surface and sanded in dry with K 120. This is repeated until the pores are closed.

After this operation, PANDOMO® TerrazzoHardener should be applied again so that sanding can continue after 8 hours.

To be noted:

Before application, the surface must be free of dust, grease, oil and other soiling. The surface must be at least dry. Any residual water on the surface must be removed. Very dry floors must be slightly pre-wetted before application.

Safety and disposal instructions:

The information in the safety data sheet must be observed.

ARDEX GmbH PO-Box 6120 · 58430 Witten GERMANY

Tel.: +49 (0) 23 02/664-0 Fax: +49 (0) 23 02/664-240

technik@ardex.de www.ardex.de

Manufacturer with QM/EM system certified in accordance with DIN EN ISO 9001/14001



PANDOMO® TerrazzoFiller

Additive for filling pores in PANDOMO® Terrazzo Systems

Technical data according to ARDEX quality standard:

Specific gravity:	approx. 1.02 g/cm ³
Material requirement:	approx. 0.05 to 0.15 litres per m2
Packing:	Canister with 20I
Storage:	in dry rooms approx. 9 months in the original sealed container storable